

# ACSR – Aluminum Conductor Steel Reinforced



Code Word	Size (AWG or kcmil)	Stranding (AL/STL)	Diameter(inch)				Weight (lbs/kft)			Content %		Rated Breaking Strength (lbs.)	Resistance** (Ohms/kft)		Ampacity* (amps)
			Individual Wire			Comp. Cable OD	AL	STL	Total	AL	STL		DC @ 20°C	AC @ 75°C	
			AL	STL	Steel Core										
Pelican	477.0	18/1	0.1628	0.1628	0.1628	0.814	447.8	70.2	518	86.45	13.55	11,800	0.0360	0.044	646
Flicker	477.0	24/7	0.1410	0.0940	0.2820	0.846	450.1	164.4	615	73.23	26.77	17,200	0.0358	0.044	655
Hawk	477.0	26/7	0.1354	0.1053	0.3159	0.858	449.6	206.4	656	68.53	31.47	19,500	0.0356	0.044	659
Hen	477.0	30/7	0.1261	0.1261	0.3783	0.883	451.1	296.2	747	60.35	39.65	23,800	0.0354	0.043	666
Osprey	556.5	18/1	0.1758	0.1758	0.1758	0.879	522.2	81.8	604	86.45	13.55	13,700	0.0308	0.038	711
Parakeet	556.5	24/7	0.1523	0.1015	0.3045	0.914	525.1	191.7	717	73.23	26.77	19,800	0.0307	0.038	721
Dove	556.5	26/7	0.1463	0.1138	0.3414	0.927	525.0	241.0	766	68.53	31.47	22,600	0.0306	0.038	726
Eagle	556.5	30/7	0.1362	0.1362	0.4086	0.953	526.3	345.6	872	60.35	39.75	27,800	0.0303	0.037	734
Peacock	605.0	24/7	0.1588	0.1059	0.3177	0.953	570.9	208.7	780	73.23	26.77	21,600	0.0282	0.035	760
Squab	605.0	26/7	0.1525	0.1186	0.3558	0.966	570.4	261.8	832	68.53	31.47	24,300	0.0281	0.035	765
Wood Duck	605.0	30/7	0.1420	0.1420	0.4260	0.994	572.0	375.6	948	60.35	39.55	28,900	0.0279	0.034	774
Teal	605.0	30/19	0.1420	0.0852	0.4260	0.994	572.0	367.4	939	60.89	39.11	30,000	0.0278	0.034	773
KingBird	636.0	18/1	0.1880	0.1880	0.1880	0.940	597.2	93.6	691	86.45	13.55	15,700	0.0270	0.033	773
Swift	636.0	36/1	0.1329	0.1329	0.1329	0.930	596.9	46.8	644	92.80	7.20	13,800	0.0271	0.033	769
Rook	636.0	24/7	0.1628	0.1085	0.3255	0.977	600.0	219.1	819	73.23	26.77	22,600	0.0268	0.033	784
Grosbeak	636.0	26/7	0.1564	0.1216	0.3648	0.990	599.9	276.2	876	68.53	31.47	25,200	0.0267	0.033	789
Scoter	636.0	30/7	0.1456	0.1456	0.4368	1.019	601.4	394.9	996	60.35	39.65	30,400	0.0256	0.033	798
Egret	636.0	30/19	0.1456	0.0874	0.4370	1.019	601.4	386.6	988	60.89	39.11	31,500	0.0266	0.033	798
Flamingo	666.6	24/7	0.1667	0.1110	0.3330	1.000	629.1	229.7	859	73.23	26.77	23,700	0.0256	0.032	807
Gannet	666.6	26/7	0.1601	0.1245	0.3735	1.014	628.7	288.5	917	68.53	31.47	26,400	0.0255	0.031	812
Stilt	715.5	24/7	0.1727	0.1151	0.3453	1.036	675.2	246.5	922	73.23	26.77	25,500	0.0239	0.029	844
Starling	715.5	26/7	0.1659	0.1290	0.3870	1.051	675.0	309.7	985	68.53	31.47	28,400	0.0238	0.029	849
Redwing	715.5	30/19	0.1544	0.0926	0.4630	1.081	676.3	434.0	1,110	60.89	39.11	34,600	0.0236	0.029	859
Coot	795.0	36/1	0.1486	0.1486	0.1486	1.040	746.2	58.5	805	92.80	7.20	16,800	0.0217	0.027	894
Cuckoo	795.0	24/7	0.1820	0.1213	0.3640	1.092	749.9	273.8	1,024	72.23	26.77	27,900	0.0215	0.027	901
Drake	795.0	26/7	0.1749	0.1360	0.4080	1.108	750.3	344.2	1,094	68.53	31.47	31,500	0.0214	0.026	907
Tern	795.0	45/7	0.1329	0.0886	0.2660	1.063	749.8	146.1	896	83.69	16.31	22,100	0.0216	0.027	887
Condor	795.0	54/7	0.1213	0.1213	0.3639	1.092	749.5	273.6	1,023	73.25	26.75	28,200	0.0215	0.027	889
Mallard	795.0	30/19	0.1628	0.0977	0.4885	1.140	751.9	483.1	1,235	60.89	39.11	38,400	0.0213	0.026	918
Chutepoke	850.0	45/7	0.1375	0.0917	0.2751	1.100	804.5	159.6	964	83.40	16.60	23,192	0.0204	0.025	935
Les Boules	864.9	42/7	0.1435	0.0797	0.2391	1.102	813.4	121.1	935	87.04	12.96	22,480	0.0201	0.025	950
Ruddy	900.0	45/7	0.1414	0.0943	0.2829	1.131	848.7	165.5	1,014	83.69	16.31	24,400	0.0191	0.024	958
Canary	900.0	54/7	0.1291	0.1291	0.3873	1.162	849.0	309.9	1,159	73.25	26.75	31,900	0.0190	0.024	961
Rail	954.0	45/7	0.1456	0.0971	0.2913	1.165	899.9	175.5	1,075	83.69	16.31	25,900	0.0180	0.023	993
Cardinal	954.0	54/7	0.1329	0.1329	0.3987	1.196	900.7	328.4	1,228	73.25	26.75	33,800	0.0179	0.023	996

All values are nominal and subject to correction.

\* Current ratings based on 75°C conductor temperature, 25°C ambient temperature, emissivity 0.5, 2ft/sec wind in sun.

\*\* Resistance is calculated using ASTM standard increments of stranding, and metal conductivity of 61.2% IACS for EC (1350) and 8% IACS for steel. AC (60Hz) resistance includes current dependent hysteresis loss factor for 1 and 3 layer constructions.